

SikaBond® T53

Elastic adhesive for wood flooring

Description	SikaBond®-T53 is a one part, elastic adhesive.
Uses	<p>For the Sika® AcouBond®-System:</p> <ul style="list-style-type: none"> ■ Solid wood boards (tongued and grooved), 3-ply engineered wood as well as chipboards can all be bonded - For detailed application instructions consult the Product Data Sheet of the Sika® AcouBond®-System, or contact our Technical Service. <p>For beaded Application:</p> <ul style="list-style-type: none"> ■ Solid wood boards (tongued and grooved), 3-ply engineered wood as well as chipboards can be bonded
Characteristics/ Advantages	<ul style="list-style-type: none"> ■ 1-part, ready to use ■ Fast curing ■ Elastic, footfall-sound-dampening adhesive ■ Suitable for common types of wood floors ■ Especially for problematic wood such as beech and bamboo ■ Suitable for bonding wood floors directly onto old ceramic tiles ■ Reduces stress on the substrate: the elastic, material-compatible adhesive reduces transverse stress between the wood floor and the substrate ■ Compensation of small substate unevenness. ■ Suitable for subfloor heating ■ Adhesive can be sanded
Product Data	
Form	
Colour	Parquet brown
Packaging	300 ml cartridges (12 cartridges per box) 600 ml Unipac (20 Unipacs per box)
Storage	
Storage Conditions/ Shelf Life	12 months from date of production if stored in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.




Table of Contents

Technical Data

Chemical Base	1-part Polyurethane, moisture curing
Density	~ 1.29 kg/l (DIN 53 479)
Skinning-/Laying Time	~ 45 - 60 minutes (23°C / 50% r.h.)
Curing Rate	~ 3.0 mm / 24h (23°C / 50% r.h.) Floor may be walked on / sanded 18 - 42 hours after installation (depending on climatic conditions and adhesive layer thickness).
Sag Flow	Consistency: Easily applicable with gun, thixotropic.
Service Temperature	-40°C to +70°C

Mechanical / Physical Properties

Shear Strength	~ 1.2 N/mm ² , 1 mm adhesive thickness (23°C / 50% r.h.) (DIN 281)
Tensile Strength	~ 1.8 N/mm ² (23°C / 50% r.h.) (DIN 53 504)
Shore A Hardness	~ 40 (after 28 days) (DIN 53 505)
Elongation at Break	~ 500% (23°C / 50% r.h.) (DIN 53 504)

System Information

Application Details

Consumption	Sika [®] AcouBond [®] -System: 580 (03) – 720 (05) g/m ² (480 - 600 ml/m ²). Filling of all cut-outs is a must. Use triangular nozzle with 8x10 mm opening. Cordon Application: Approx. 44 ml per running meter = 200 - 400 g/m ² , dependent on cordon interval (solid wood boards, 3-ply engineered wood, chipboards).
--------------------	--

Substrate Quality	Clean and dry, homogeneous, even, free from grease, dust and loose particles. Paint, laitance and other poorly adhering particles must be removed. Standard construction rules must be observed.
--------------------------	--

Substrate Preparation	Concrete / cement screed: Must be ground and thoroughly cleaned with industrial vacuum cleaner. Anhydrite screed / Anhydrite flowable screed: Must be ground and thoroughly cleaned with industrial vacuum cleaner shortly before bonding starts. Broadcast mastic asphalt: Must be primed with Sika [®] Primer MB. Instructions for use, see Product Data Sheet for Sika [®] Primer MB. Glazed ceramic and old ceramic tiles: Degrease, clean with SikaCleaner [®] or grind the tile-surface and clean thoroughly with an industrial vacuum cleaner. Wood / gypsum boards (e.g. chipboards, plywood): Glue / screw the boards to the substructure. They have to be fixed on the substrate. In case of floating subfloors, please contact our Technical Service. Unknown substrates: Please contact our Technical Service. SikaBond [®] -T53 can be used without priming on cement floors, anhydrite floors, chip boards, concrete and ceramic tiles. For broadcast mastic asphalt, cement floors with an excessive moisture content, as well in case of renovation on old adhesive residues and on structurally weak substrates use Sika [®] Primer MB. For detailed instructions consult the Product Data Sheet of Sika [®] Primer MB or contact our Technical Service.
------------------------------	--

Application Conditions / Limitations	
Substrate Temperature	<p>During laying and until SikaBond®-T53 has fully cured substrate temperature must be > +15°C and in case of floor heating < +20°C.</p> <p>For Substrate temperatures the standard construction rules are relevant.</p>
Ambient Temperature	<p>Room temperature between +15°C and +35°C.</p> <p>For ambient temperatures the standard construction rules are relevant.</p>
Substrate Humidity	<p>Permissible substrate moisture content:</p> <ul style="list-style-type: none"> ■ 2.5% CM for cement screed (ca. 4% Tramex / Gravimetric weight percent) ■ 0.5% CM for anhydrite screed ■ 3-12% CM for magnesia flooring (proportion of organic parts) <p>Permissible substrate moisture content in case of floor heating:</p> <ul style="list-style-type: none"> ■ 1.8% CM for cement screed (ca. 3% Tramex / Gravimetric weight percent) ■ 0.3% CM for anhydrite screed ■ 3-12% CM for magnesia flooring (proportion of organic parts) <p>For moisture content and quality of substrates the guidelines of wood floor manufacturer as well as standard construction rules must be observed.</p>
Relative Air Humidity	Between 40% and 70%
Application Instruction	
Application Method / Tools	<p>Sika® AcouBond®-System: For detailed application instructions consult the Product Data Sheet of the Sika® AcouBond®-System, or contact our Technical Service.</p> <p>Cordon Application: After the preparation of sausage and gun, extrude a triangular shaped cordon of adhesive approximately 10 mm high and 8 mm wide at 100-250 mm centres (dependent on wood floor type) on the properly prepared subfloor. Press the wood floor elements firmly in to the adhesive (at right angles with adhesive cordons). The elements can then be joined together using a hammer and a impact block. The required distance from the wall to the wood floor in the laying instruction from the wood floor manufacturer must be observed.</p> <p>Fresh, uncured adhesive remaining on the wood floor surface must be removed immediately with a clean cloth and if necessary cleaned with Sika® Remover-208 or Sika® TopClean-T towels. Test wood floor surfaces for compatibility before use.</p> <p>The laying instructions of the wood floor manufacturer as well as standard construction rules must be observed.</p>
Cleaning of Tools	Clean all tools and application equipment with Sika® Remover-208 / Sika® TopClean-T immediately after use. Hardened / cured material can only be removed mechanically.

Notes on Application / Limitations

Wood floor adhesives must only be used by experienced applicators.

If, according to wood floor suppliers or producers deviation from the standards is permissible, temperatures between +5°C and +35°C must be observed for the adhesive.

For better workability the adhesive temperature must be at least +15°C.
For the proper curing of the adhesive sufficient ambient moisture is necessary.

For AcouBond-System and Cordon Application accurate tongue and groove (min. 3x3 mm) are inevitable:

Minimum wood size:	length	>300 mm (over 3 adhesive cordons)
	width	> 50 mm
	thickness	> 12 mm
Maximum wood size:	thickness	< 28 mm

Wood floors in non insulated areas such as basements, or other areas without a damp proof membrane, can only be installed after the application of Sikafloor® EpoCem and Sika® Primer MB to control the moisture. For detailed instructions consult the Product Data Sheets or contact our Technical Service.

In case of chemically pre-treated types of wood floors (e.g. ammonia, wood stain, timber preservative) and woods with high oil content SikaBond®-T53 is only to be used after a written recommendation from our Technical Service.

Do not use on PE, PP, TEFLON, and certain plastized synthetic materials (carry out pre-trials or contact our Technical Service).

Some primers can negatively influence the adhesion of SikaBond®-T53 (pre trials recommended).

When laying bonded wood flooring, always make sure that any wood surface sealer coatings do not come into contact with the adhesive. However if direct contact with the adhesive is unavoidable, then the compatibility of the sealing coats must always be checked and confirmed before use. For further information or assistance please contact your local Sika Technical Service Department.

Do not mix with or expose uncured SikaBond®-T53 to substances that may react with isocyanates, especially alcohols which are often components within e.g. thinners, solvents, cleaning agents and formwork releasing compounds. Such contact could interfere or prevent the cross linking curing reaction of the material.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control

Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the product when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia
 Jl. Raya Cibinong- Bekasi km. 20
 Limusunggal- Cileungsi
 BOGOR 16820 - Indonesia
 Tel. +62 21 8230025
 Fax +62 21 8230025
 Website : www.sika.co.id
 e-mail: sikacare@id.sika.com

Branches
 Surabaya :
 Puri Niaga Blok G No. 29, Jl. Raya Rungkut Menanggal 11, Surabaya
 Tel : 031-8690202 ; Fax : 031-8682123
 Medan :
 Jl. Pancing / Jl. Willem Iskandar No.75 & 75 A, Kec. Medan Tembung
 Tel : 061- 6619500; Fax : (061) 6619400
 Batam :
 Jl. Laksamana Bintang, Komp. Bumi Riau Makmur Blok E No.3, Sungai Panas
 Tel : (0778) 424928; Fax : (0778) 450189

